

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 288 319 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
05.03.2003 Bulletin 2003/10

(51) Int Cl.7: C22B 21/06, C22B 9/00

(21) Application number: 01203312.2

(22) Date of filing: 03.09.2001

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR
Designated Extension States:
AL LT LV MK RO SI

(72) Inventor: De Vries, Paul Alexander
2102 GM Heemstede (NL)

(74) Representative: Hansen, Willem Joseph Maria
Corus Technology BV
Corus Intellectual Property Department
PO Box 10000
1970 CA IJmuiden (NL)

(71) Applicant: Corus Technology BV
1970 CA IJmuiden (NL)

(54) Method for the purification of an aluminium alloy

(57) Method for the purification of an aluminium alloy containing an alloying element wherein the aluminium alloy is subjected to a fractional crystallisation process wherein at least the aluminium alloy is separated into a product stream having a content of the alloying element less than the content of the alloying element in the aluminium alloy and a downgrade stream having a content of the alloying element higher than the content of the alloying element in the aluminium alloy and wherein the downgrade stream is subjected to a process of separation of intermetallics wherein an additive is added to the downgrade stream to form a mixture containing intermetallics formed and from this mixture a waste stream and a recycle stream is separated which waste stream contains a higher content of the alloying element than the recycle stream and the recycle stream is fed at least partly into the fractional crystallisation process.




Fig. 2

EP 1 288 319 A1

Description

[0001] The invention relates to a method for the purification of an aluminium alloy.

[0002] A known method is fractional crystallisation, which can be applied to purify e.g. an aluminium alloy contaminated with an alloying element such as iron. In fractional crystallisation an input stream of an aluminium alloy scrap material, which, for a certain alloying element or contaminant, is hypoeutectic in composition, is split into a first output stream or product stream of purified aluminium and a second output stream or downgrade stream, which is more contaminated with the contaminant than the input stream and has a composition closer to the eutectic composition for the contaminant.

[0003] Where in this description reference is made to fractional crystallisation, this is to be understood as comprising all forms of fractional crystallisation and all other purification methods starting from a hypoeutectic alloy, whereby the composition of the downgrade stream is determined by the eutectic composition of aluminium and an alloying element.

[0004] A problem of fractional crystallisation is that the maximum content of contaminant in the downgrade stream is determined by the eutectic composition. In the event of an input stream of aluminium contaminated with 0.5% Fe, and a Fe content of the product stream of less than 0.1%, the downgrade stream, having an increased Fe content, is more than 25% of the input stream.

[0005] As can readily be seen from the Al-Fe phase diagram, the purer the product stream is made, the less contaminated the downgrade stream will be. However, for an economic process a low volume of a highly contaminated downgrade stream is desirable.

[0006] The performance of a basic fractional crystallisation process can be improved by using a multistage or counter current fractional crystallisation process but the limit for the contamination of the downgrade stream with the alloying element is determined by the eutectic composition.

[0007] In general, the material of the product stream has a higher economic value than the material of the original aluminium alloy, whereas the material of the downgrade stream has a lower economic value. In the present market for the most common aluminium alloys, the loss in value of the higher contaminated downgrade stream, as compared to the value of the original aluminium alloy, is not compensated by the increase of the economic value of the product stream. The demand in the market for the material of the downgrade stream from the fractional crystallisation process is fairly low, so if it would be produced in large amounts, the economic value thereof will drop fast. Therefore, the process of fractional crystallisation, or in fact any other separation process wherein the input waste stream results in a more purified and a more contaminated stream of eutectic or near eutectic composition is to date economically not feasible.

[0008] An object of the invention is to provide a method for the purification of an aluminium alloy that is economically more feasible. This and other objects are achieved with a method for the purification of an aluminium alloy containing an alloying element or contaminant wherein the aluminium alloy is subjected to a fractional crystallisation process wherein at least the aluminium alloy is separated into a product stream having a content of the alloying element less than the content of the alloying element in the aluminium alloy and a downgrade stream having a content of the alloying element higher than the content of the alloying element in the aluminium alloy and wherein the downgrade stream is subjected to a process of separation of intermetallics wherein an additive is added to the downgrade stream to form a mixture containing aluminium-alloying element-additive intermetallics and from this mixture a waste stream and a recycle stream is separated which waste stream contains a higher content of the alloying element than the recycle stream and the recycle stream is at least partly fed into the fractional crystallisation process. The method according to the invention combines a hypoeutectic process, like fractional crystallisation (FC), with a hypereutectic process, like separation of intermetallics (SIM). The waste stream comprises solid Al-alloying element-additive intermetallics, the recycle stream is basically a liquid aluminium stream containing less of the alloying element than the downgrade component. A frequently occurring alloying element is Fe.

[0009] The principle of SIM processes is known in the art of metallurgy and comprises such processes as layer crystallisation, filtration, magnetic separation, hydro cyclonage and precipitation in molten salts.

[0010] The downgrade stream of the FC process is used as an input stream for the SIM process. In this SIM process an additive is added. The additive is selected such that it effectively lowers the eutectic composition of the alloying element and aluminium such as the eutectic composition of Fe and aluminium.

[0011] The downgrade stream of the fractional crystallisation process is made into a hypereutectic mixture by adding the additive thereto. In the SIM process the mixture is split into a waste stream with a high content of the additive and the alloying element and a recycle stream with a lower composition of the alloying element. This recycle stream is mixed with the input stream of the aluminium alloy.

[0012] The method of the invention opens a new, much more economic, way to the purification of aluminium alloys, in particular suitable for aluminium alloys of a composition typical in the field of scrap recycling.

[0013] Other advantages of the method are the economy of volume, synergetic advantages by process integration, lower sensitivity to variation of aluminium prices and environmental sustainability. The method stays economically

profitable even when applied on a very large scale.

[0014] The method of the invention uses the separation of intermetallics process to purify the downgrade of the FC process and the FC process to purify at least part of the product stream (recycle stream) of the SIM process. The fundamental impossibility to cross the eutectic for the FC process and the SIM process separately is circumvented by introducing a recycle loop in the process of the invention. The, nearer to the eutectic, downgrade stream of the FC process is made hypereutectic by adding the additive. The, nearer to the eutectic, product stream (recycle stream) of the SIM process is made hypoeutectic by diluting the additive through addition of aluminium alloy material to be purified. The result of the process is at least partial removal of the alloying element from the aluminium alloy with a small resulting waste stream with a content of the alloying element above eutectic.

[0015] For economic reasons, a smaller, highly impure waste stream is preferred over a larger less contaminated waste stream. However, Al-Fe- additive intermetallics contain a high amount of aluminium. In the usual, separately applied, process of separation of intermetallics, the solid-liquid separation would imply an even greater loss of aluminium. Also, the waste stream is not particularly valuable. It contains quite substantial amounts of iron, making it applicable to low-end uses only. Further, the product stream (recycle stream) of the separation of intermetallic process, which is the purified stream, is near eutectic in composition. There is only a very small market for an aluminium alloy comprising a, near, eutectic amount of the alloying element such as Fe in aluminium. Consequently, the present market cannot absorb the offered amount leading to a low price, which makes the process not feasible for large-scale industrial application. For these reasons, also the SIM process, when applied separately, is not economically feasible.

[0016] Different from this, the process of the invention only produces a small waste stream. Therefore, it does not suffer from the problems described above that the waste stream of each of the separate processes, SIM process and FC process, is large compared to the demand in the market. Hence, large-scale application of the process of the invention only to a small extent influences the value of the waste stream and the profitability of the total process.

[0017] The mass balance of the process of the invention may limit the proportion of the product stream from the SIM process that can be fed back into the fractional crystallization process as recycle. Part of the liquid product stream then remains with the intermetallics formed. Preferably, at least part of the liquid aluminium is separated from the intermetallics in a subsequent separation process.

[0018] As mentioned above, the fractional crystallisation process in itself is not at present economic, in particular not for high volume applications.

[0019] However, by combining the two processes according to the invention a highly purified product stream and a waste stream, smaller than in the separate processes, containing a large quantity of the alloying element and the additive is obtained. This small waste stream can be used e.g. as a de-oxidising or alloying agent in the steel making industry or the intermetallics can be decomposed by electrolysis and the constituents can be recovered. The product stream is a high value starting material for high quality aluminium alloys. Therefore, the combination of two, in themselves not economically feasible, processes into one combined process leads to an economically feasible, new and inventive process.

[0020] A preferred embodiment is characterised in that the additive comprises at least one element chosen from Si, Mn, Cu, Co and Ni. These elements as additive, added either individually or in combination, easily form intermetallics with many alloying elements used in the aluminium industry and yield a high removal efficiency. This applies in particular but not restricted thereto when the alloying element to be removed is Fe.

[0021] A further embodiment is characterised in that the additive comprises mainly Mn. When using mainly Mn as the additive, a considerable reduction in the amount of waste stream can be obtained, in particular but not restricted thereto in the event that the alloying element is Fe.

[0022] The invention is of particular interest in the event the alloying element is Fe.

[0023] Contamination of aluminium by iron occurs during use or manufacture of aluminium products or accumulates in other recycle processes. Iron has an adverse effect on formability and fracture mechanics of aluminium alloy products and therefore can only be tolerated in small amounts.

[0024] Preferably, when Fe is the alloying element to be removed, the Fe content in the aluminium alloy is less than 1.7 weight %, more preferably 1.5 weight %. In case the Fe content is still closer to the eutectic value, the possible increase of Fe content in the downgrade stream of the FC process compared to the Fe content in the input stream is too low to make the overall process economically feasible.

[0025] Preferably, when Fe is the alloying element to be removed is more than 0.4 weight %, more preferably more than 0.5% Fe.

[0026] At lower Fe content of the input stream of the aluminium alloy to be purified, no substantial decrease of the amount of the waste stream is obtained since the recycle stream from the SIM process contains, dependent on the additive used, also about 0.5% Fe.

[0027] The invention will be illustrated by comparing the amount and composition of a waste stream and product stream for the fractional crystallisation process and the process of our invention.

[0028] In Table 1 the composition of an aluminium alloy is given. The mass is assumed to be one unit, e.g. 1000 kg.

Table 1:

aluminium alloy (scrap) composition				
	mass	wt% Al	wt% Fe	wt% Mn
scrap	1.000	99.50	0.50	0.00

For the case that the scrap is purified using the FC process, the resulting product stream and waste stream compositions and masses are given in Table 2. As can be seen, the waste mass is about 25% of the original scrap mass.

Table 2:

product and waste mass and composition by applying FC to the scrap of Table 1				
FC	mass	wt% Al	wt% Fe	wt% Mn
product	0.754	99.94	0.06	0.00
waste	0.246	98.15	1.85	0.00

[0029] Table 3 shows the result when our invention is applied to the scrap by adding an additive like manganese to the downgrade stream of the FC process and feeding back at least part of the product stream from the SIM process as recycle to the input of the FC process. The table shows that the waste is reduced to less than 17% of the input scrap mass. It is assumed that at least the intermetallic Al₆ [Fe, Mn] is formed.

[0030] The waste, according to Table 3, is about 17% of the input mass. The amount of recycle that can be fed back into the FC process is determined by mass balance consideration and in many cases does not comprise the total amount of product from the SIM-process.

[0031] The amount of waste can be further reduced by further separating in a separate process aluminium, preferably in liquid form, from the intermetallics.

[0032] Adding an additional separating process also has the advantage of a greater flexibility in the selection of the applied SIM-process. A less effective SIM-process, having a lower separation capability, but at lower costs can be applied. Further separation can then be performed by the additional separation process.

Table 3:

Product, waste and additive mass by applying the process of the invention to the scrap of Table 1				
XEP	mass	wt% Al	wt% Fe	wt% Mn
product	0.839	99.91	0.06	0.03
waste	0.167	93.70	2.70	3.60
additive	0.006	0.00	0.00	100.00

[0033] The invention will now be illustrated with reference to the drawing in which Fig. 1 shows the principle of the invention and Fig. 2 shows in a diagrammatic representation of an embodiment of the invention.

[0034] In Fig. 1 the basic processes of the method of the invention are enclosed by square 20. The processes comprise a FC process, indicated by numeral 21, and a SIM process, indicated by numeral 22. Scrap to be cleaned indicated by numeral 23 is fed through a line 24 into the FC process 21. The obtained purified product is indicated by numeral 25 and is removed from the FC process through line 26. The downgrade 27 is exported from the FC process through line 28 and fed into the SIM process 22 through line 29. A waste component 30 from the SIM process is taken from the SIM process through line 31. Additive 32 is fed into the SIM process through line 33. The recycle component 34 is taken from SIM process 22 through line 35 and fed into the FC process through line 36.

[0035] In Fig. 2 reference number 11 indicates a supply line through which a stream of an aluminium alloy, as scrap, preferably in molten form, containing an alloying element is fed to a first process vessel 12 in which the fractional crystallisation process is performed. This fractional crystallisation process may be chosen to be a known embodiment of fractional crystallisation. Connected to supply line 11 is a return line 13 the function of which will be described later. The supply line 11 and return line 13 merge into an input line 19, which is coupled to process vessel 12. In the fractional crystallisation process the mixture of aluminium alloy and downgrade stream is separated into a product component, which is removed through product line 14, and a residual component that is extracted from process vessel 12 through waste line 15. Waste line 15 is connected to a second process vessel 17, to which also a feed line 16 is connected.

Through feedline 16, an additive, such as Mn, is fed into the second process vessel 17. A separation of intermetallics process is performed in second process vessel 17. A waste stream, containing a high quantity of the alloying element, such as Fe, and also containing Mn, is removed through waste line 18. Also connected to second process vessel 17 is the return line 13 through which a, purified, off-stream of the second process is fed back as a recycle into process vessel 12.

[0036] Optionally, the waste stream is fed through line 18 into a subsequent separation process 10 in which aluminium, in liquid or solid form, is separated from intermetallics. By this additional separation process the amount of waste removed through line 9 can be further reduced and a higher amount of purified aluminium, taken out through line 8, can be obtained.

[0037] The total combined process has as input-streams the stream of aluminium alloy to be cleaned, and the stream of additive and as output-stream the waste stream and the product component.

Claims

1. Method for the purification of an aluminium alloy containing an alloying element wherein the aluminium alloy is subjected to a fractional crystallisation process wherein at least the aluminium alloy is separated into a product stream having a content of the alloying element less than the content of the alloying element in the aluminium alloy and a downgrade stream having a content of the alloying element higher than the content of the alloying element in the aluminium alloy and wherein the downgrade stream is subjected to a process of separation of intermetallics wherein an additive is added to the downgrade stream to form a mixture containing intermetallics formed and from this mixture a waste stream and a recycle stream is separated which waste stream contains a higher content of the alloying element than the recycle stream and the recycle stream is fed at least partly into the fractional crystallisation process.
2. Method according to any of the preceding claims, wherein the additive comprises at least one element chosen from Si, Mn, Cu, Co and Ni.
3. Method according to any of the preceding claims, wherein the additive comprises mainly Mn.
4. Method according to any of the preceding claims, wherein the alloying element is Fe.
5. Method according to claim 4, wherein the Fe content in the aluminium alloy is less than 1.7 weight %, preferably less than 1.5 weight%.
6. Method according to claim 4 or 5, wherein the Fe content in the aluminium alloy is more than 0.4 weight%, preferably more than 0.5 weight%.




Fig. 1




Fig. 2



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 20 3312

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	PATENT ABSTRACTS OF JAPAN vol. 1995, no. 06, 31 July 1995 (1995-07-31) - & JP 07 070666 A (NIPPON LIGHT METAL CO LTD; OTHERS: 01), 14 March 1995 (1995-03-14) * abstract *	1-6	C22B21/06 C22B9/00
A	US 4 273 627 A (DAWLESS ROBERT K ET AL) 16 June 1981 (1981-06-16) * the whole document *	1-6	
A	EP 0 745 693 A (HOOGOVENS ALUMINIUM BV) 4 December 1996 (1996-12-04) * the whole document *	1-6	
A	PATENT ABSTRACTS OF JAPAN vol. 004, no. 085 (C-015), 18 June 1980 (1980-06-18) - & JP 55 050442 A (KOBE STEEL LTD), 12 April 1980 (1980-04-12) * abstract *	1-6	
A	PATENT ABSTRACTS OF JAPAN vol. 010, no. 103 (C-340), 18 April 1986 (1986-04-18) - & JP 60 234930 A (TOYOTA JIDOSHA KK), 21 November 1985 (1985-11-21) * abstract *	1-6	
A	US 4 411 747 A (DAWLESS ROBERT K ET AL) 25 October 1983 (1983-10-25) * the whole document *	1-6	
A	US 4 456 480 A (WINTENBERGER MICHEL G) 26 June 1984 (1984-06-26) * the whole document *	1-6	
-/-			
The present search report has been drawn up for all claims			
Place of search		Date of completion of the search	Examiner
MUNICH		22 October 2001	Patton, G
CATEGORY OF CITED DOCUMENTS		T : theory of principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application I : document cited for other reasons & : member of the same patent family, corresponding document	
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			

EPD FORM 1503 03.82 (P04001)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 20 3312

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl. 7)
A	EP 0 375 308 A (ALCAN INT LTD) 27 June 1990 (1990-06-27) * the whole document *	1-6	
A	US 4 744 823 A (RAYMOND-SERAILLE ANDRE) 17 May 1988 (1988-05-17) * the whole document *	1-6	
			TECHNICAL FIELDS SEARCHED (Int.Cl. 7)
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 22 October 2001	Examiner Patton, G
CATEGORY OF CITED DOCUMENTS		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date O : document cited in the application L : document cited for other reasons A : technical background Q : non-written disclosure P : prior art document	
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category		& : member of the same patent family, corresponding document	

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 20 3312

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

22-10-2001

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
JP 07070666	A	14-03-1995	NONE		
US 4273627	A	16-06-1981	US	4222830 A	16-09-1980
			AU	522960 B2	01-07-1982
			AU	4910779 A	03-07-1980
			CA	1138374 A1	28-12-1982
			CH	643000 A5	15-05-1984
			DE	2951720 A1	03-07-1980
			FR	2445380 A1	25-07-1980
			GB	2039529 A ,B	13-08-1980
			HU	182924 B	28-03-1984
			IT	1164789 B	15-04-1987
			JP	1489436 C	23-03-1989
			JP	55089440 A	07-07-1980
			JP	58013613 B	15-03-1983
			NL	7909254 A	30-06-1980
			NO	793951 A ,B	27-06-1980
			NZ	192376 A	19-11-1981
EP 0745693	A	04-12-1996	NL	1000456 C2	03-12-1996
			CA	2177666 A1	01-12-1996
			EP	0745693 A1	04-12-1996
			JP	9111359 A	28-04-1997
			NO	962213 A	02-12-1996
			US	5741348 A	21-04-1998
JP 55050442	A	12-04-1980	JP	1337849 C	29-09-1986
			JP	59012731 B	26-03-1984
JP 60234930	A	21-11-1985	JP	1373471 C	07-04-1987
			JP	51039385 B	03-09-1986
US 4411747	A	25-10-1983	AU	554919 B2	04-09-1986
			AU	1811683 A	08-03-1984
			BR	8304679 A	10-04-1984
			CA	1245178 A1	22-11-1988
			CH	658259 A5	31-10-1986
			JP	1406626 C	27-10-1987
			JP	59047393 A	17-03-1984
			JP	62010315 B	05-03-1987
US 4456480	A	26-06-1984	FR	2524489 A1	07-10-1983
			AT	14321 T	15-08-1985
			AU	551208 B2	17-04-1986
			AU	1296583 A	06-10-1983
			BR	8301580 A	06-12-1983

1288319A1

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 20 3312

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

22-10-2001

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4456480	A		CA 1186156 A1	30-04-1985
			DE 3360397 D1	22-08-1985
			EP 0091386 A1	12-10-1983
			ES 520918 D0	16-01-1984
			ES 8402357 A1	16-04-1984
			SR 77983 A1	25-09-1984
			IN 158125 A1	13-09-1986
			JP 1350563 C	28-11-1986
			JP 58181834 A	24-10-1983
			JP 61016413 B	30-04-1986
			KR 8501739 B1	07-12-1985
			NO 831164 A ,B,	03-10-1983
			NZ 203682 A	24-01-1986
			ZA 8302268 A	28-12-1983
EP 0375308	A	27-06-1990	AU 4703289 A	28-06-1990
			EP 0375308 A1	27-06-1990
			JP 2225633 A	07-09-1990
US 4744823	A	17-05-1988	FR 2592663 A1	10-07-1987
			AT 56480 T	15-09-1990
			AU 580521 B2	12-01-1989
			AU 6691186 A	09-07-1987
			BR 8700007 A	01-12-1987
			CA 1287217 A1	06-08-1991
			CN 87100033 A ,B	22-07-1987
			DD 253049 A5	06-01-1988
			DE 3764829 D1	18-10-1990
			DK 1287 A	07-07-1987
			EP 0236238 A1	09-09-1987
			HK 23692 A	10-04-1992
			IL 81129 A	15-12-1989
			IN 168687 A1	18-05-1991
			JP 1656763 C	13-04-1992
			JP 3022453 B	26-03-1991
			JP 62158830 A	14-07-1987
			KR 9006697 B1	17-09-1990
			NO 870024 A ,B,	07-07-1987
			NZ 218824 A	26-04-1990
			PH 22854 A	19-01-1989
			SG 49991 G	13-09-1991
			SU 1732817 A3	07-05-1992
			ZA 8700038 A	30-03-1988

EPO FORM P369

For more details about this annex, see Official Journal of the European Patent Office, No. 12/82